

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>Other Standards<sup>[5]</sup></b>			
Melt flow index, MFI	8.5	g/10min	
Temperature	220	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.6	%	

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
<b>Other Standards<sup>[5]</sup></b>			
Yield stress	42	MPa	
Charpy impact strength, +23°C	25	kJ/m <sup>2</sup>	

S: These properties are reported by the producer according standards that are different to our defaults.

Thermal properties	Value	Unit	Test Standard
<b>Other Standards<sup>[5]</sup></b>			
Vicat softening temperature, B	98.5	°C	

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Color b	-0.5	-	CIE
<b>Other Standards<sup>[5]</sup></b>			
Density	1050	kg/m <sup>3</sup>	

S: These properties are reported by the producer according standards that are different to our defaults.

## Characteristics

### Special Characteristics

High impact or impact modified

### Regional Availability

Asia Pacific

### Certifications

Food contact, Food approval FDA 21 CFR