

**A6060B**

ABS

Pontex Polyblend Co., Ltd.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>5</b>	g/10min	ASTM D 1238
Mold Shrinkage, MD	<b>0.45</b>	mm/mm	ASTM D 955

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength	<b>16.7</b>	MPa	ASTM D 638
Flexural Modulus	<b>3433</b>	MPa	ASTM D 790
Flexural Strength	<b>34.3</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>19.6</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
DTUL @ 264 psi	<b>70</b>	°C	ASTM D 648

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1800</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Features**

High Gloss

**Regional Availability**

Asia Pacific