

ABS 4125

ABS

MBA Polymers

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	8	g/10min	ISO 1133
Temperature	230	°C	-
Load	3.8	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	40	MPa	ISO 527
Flexural modulus, 23°C	2050	MPa	ISO 178
Izod notched impact strength, +23°C	13	kJ/m ²	ISO 180/1A

Other properties	Value	Unit	Test Standard
Density	1050	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.1	%	-
Melt temperature	210 - 230	°C	-
Mold temperature	40 - 60	°C	-

Characteristics**Processing**

Injection Molding, Other Extrusion

Special Characteristics

High impact or impact modified

Features

Copolymer

Certifications

Recycled Resin Content

Regional Availability

North America, Europe, Asia Pacific