

ABS BM662

ABS

LG Chem

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	4.4	g/10min	ASTM D 1238
Temperature	220	°C	-
Load	10	kg	-
Mold Shrinkage, MD	0.0055	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	47.1	MPa	ASTM D 638
Elongation at Break	20	%	ASTM D 638
Flexural Modulus	2256	MPa	ASTM D 790
Flexural Strength	69.7	MPa	ASTM D 790
Rockwell Hardness	R 102	-	ASTM D 785
Izod Impact notched, 1/8 in	189	J/m	ASTM D 256
Izod Impact notched, 1/4 in	207	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	94.3	J/m	ASTM D 256
Temperature	-30	°C	-

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	100	°C	ASTM D 648
DTUL @ 264 psi	93	°C	ASTM D 648
Vicat Temperature	100	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	1050	kg/m ³	ASTM D 792

Processing Recommendation Extrusion	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 90	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.01	%	-
Melt temperature	200 - 210	°C	-
Zone 1	180 - 200	°C	-
Zone 2	190 - 210	°C	-
Zone 3	190 - 210	°C	-
Zone 4	200 - 220	°C	-
Nozzle temperature	220	°C	-

Characteristics**Processing**

Blow Molding

Special Characteristics

Heat stabilized or stable to heat

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific, South and Central America