

**ABS TR300**

ABS

LG Chem

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	25	g/10min	ASTM D 1238
Temperature	220	°C	-
Load	10	kg	-
Mold Shrinkage, MD	0.0055	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Modulus	2305	MPa	ASTM D 638
Tensile Strength at Yield	46	MPa	ASTM D 638
Elongation at Yield	5	%	ASTM D 638
Elongation at Break	20	%	ASTM D 638
Flexural Modulus	2207	MPa	ASTM D 790
Flexural Strength	72	MPa	ASTM D 790
Rockwell Hardness	R 107	-	ASTM D 785
Izod Impact notched, 1/8 in	137	J/m	ASTM D 256
Izod Impact notched, 1/4 in	127	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	39	J/m	ASTM D 256
Temperature	-30	°C	-

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 66 psi	92	°C	ASTM D 648
DTUL @ 264 psi	84	°C	ASTM D 648
Vicat Temperature	91	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	1180	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 90	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.01	%	-
Melt temperature	190 - 210	°C	-
Mold temperature	50 - 80	°C	-
Zone 1	170 - 190	°C	-
Zone 2	180 - 200	°C	-
Zone 3	190 - 210	°C	-
Nozzle temperature	190 - 210	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.5 - 0.8	MPa	-

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

Flame retardant, Transparent

**Applications**

IT / Business Machine, Electrical and Electronical

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America