

**ABS40**

ABS

Persian Gulf Polymer Pooya Tejarat Novin Co.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	25	g/10min	ASTM D 1238
Temperature	220	°C	-
Load	10	kg	-
Mold Shrinkage, MD	0.0055	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength	39.2	MPa	ASTM D 638
Flexural Modulus	1766	MPa	ASTM D 790
Flexural Strength	56.9	MPa	ASTM D 790
Rockwell Hardness	R 98	-	ASTM D 785

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	HB	-	UL 94
DTUL @ 264 psi	82	°C	ASTM D 648
Vicat Temperature	92	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	1040	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Special Characteristics**

High impact or impact modified

**Applications**

Automotive, General Purpose, Sports Equipment

**Regional Availability**

Europe, Asia Pacific, South and Central America, Near East/Africa