

**Absolac® 200EP**

ABS

Styrenix Performance Materials Limited

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	20	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.005	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Rockwell hardness	R 102	-	ISO 2039-2
<b>ASTM Data</b>			
Tensile Modulus	2551	MPa	ASTM D 638
Tensile Strength at Yield	44.1	MPa	ASTM D 638
Flexural Modulus	2060	MPa	ASTM D 790
Flexural Strength	61.3	MPa	ASTM D 790
Rockwell Hardness	R 102	-	ASTM D 785
Izod Impact notched, 1/8 in	343	J/m	ASTM D 256
Izod Impact notched, 1/4 in	294	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Coefficient of Thermal Expansion, MD	85	E-6/K	ASTM D 696
DTUL @ 66 psi	95	°C	ASTM D 648
DTUL @ 264 psi	93	°C	ASTM D 648
Vicat Temperature	95	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	1040	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	220 - 260	°C	-
Mold temperature	60 - 80	°C	-

**Characteristics****Processing**

Injection Molding

**Features**

Copolymer

**Delivery form**

Pellets

**Regional Availability**

Asia Pacific

**Special Characteristics**

Platable