

ABWH2 WHITE

ABS

Persian Gulf Polymer Pooya Tejarat Novin Co.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	32	g/10min	ASTM D 1238
Temperature	220	°C	-
Load	10	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	4300	MPa	ASTM D 638
Tensile Strength at Yield	43	MPa	ASTM D 638
Tensile Strength at Break	38	MPa	ASTM D 638
Flexural Modulus	2100	MPa	ASTM D 790
Shore D Hardness	79	-	ASTM D 2240

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	88	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1060	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Delivery form

White

Special Characteristics

High impact or impact modified

Features

Copolymer

Certifications

Recycled Resin Content

Applications

Automotive, General Purpose

Regional Availability

Europe, Asia Pacific, South and Central America, Near East/Africa