

Product Texts

Base Polymer	Acrylonitrile/Butadiene/Styrene/Copolymer
Colour	metallic effect
Special Features	low tendency to flow lines,easy flow
Market Segment	electrical and electronic,building and construction
Application Area	domestic appliances
Typical Applications	housings

Processing/Physical Characteristics

	Value	Unit	Test Standard
--	-------	------	---------------

ISO Data

^[C] Melt volume-flow rate, MVR	35	cm ³ /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-

[C]: CAMPUS

Mechanical properties

	Value	Unit	Test Standard
--	-------	------	---------------

ISO Data

^[C] Tensile Modulus	2500	MPa	ISO 527
^[C] Yield stress	38	MPa	ISO 527
^[C] Yield strain	2.2	%	ISO 527
^[C] Charpy impact strength, +23°C	20	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties

	Value	Unit	Test Standard
--	-------	------	---------------

ISO Data

^[C] Temp. of deflection under load, 1.80 MPa	85	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	95	°C	ISO 306

[C]: CAMPUS

Other properties

	Value	Unit	Test Standard
--	-------	------	---------------

^[C] Density	1080	kg/m ³	ISO 1183
------------------------	------	-------------------	----------

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Applications

Building Construction, Electrical and Electronical, Encapsulation

Features

Metallic effect, Copolymer

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information**Injection molding**

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-4 h 80 °C in an air circulating dryer for 3-6 h dependant on moisture content
Processing Injection Moulding	melt temperature 220-260 °C mould temperature 50-80 °C
Storage	dry, protected from light not above 30°C