

**Product Texts**

Base Polymer	Acrylonitrile/Butadiene/Styrene/Copolymer
Special Features	medium viscosity
Market Segment	various
Application Area	domestic appliances, electrical and electronic (E&E)
Typical Applications	housings

**Processing/Physical Characteristics**

	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	18	cm <sup>3</sup> /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-

[C]: CAMPUS

**Mechanical properties**

	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	2400	MPa	ISO 527
<sup>[C]</sup> Yield stress	44	MPa	ISO 527
<sup>[C]</sup> Yield strain	2.4	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	90	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	20	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

**Thermal properties**

	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	85	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	95	°C	ISO 306

[C]: CAMPUS

**Other properties**

	Value	Unit	Test Standard
<sup>[C]</sup> Density	1040	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Features**

Copolymer

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

**Other text information****Injection molding**

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-4 h 80 °C in an air circulating dryer for 3-6 h dependant on moisture content
Processing Injection Moulding	melt temperature 220-260 °C mould temperature 50-80 °C
Storage	dry, protected from light not above 30°C