

**Product Texts**

Base Polymer	Acrylonitrile/Butadiene/Styrene/Copolymer
Special Features	good flow, processing stabilised, injection moulding grade
Market Segment	electrical and electronic, building and construction, Medical / Personal Care, various
Application Area	ducting / piping systems, domestic appliances, valve components, various
Typical Applications	housings, printer housings, paper dispensers, operating elements, various

**Processing/Physical Characteristics**

	Value	Unit	Test Standard
--	-------	------	---------------

**ISO Data**

<sup>[C]</sup> Melt volume-flow rate, MVR	28	cm <sup>3</sup> /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-

[C]: CAMPUS

**Mechanical properties**

	Value	Unit	Test Standard
--	-------	------	---------------

**ISO Data**

<sup>[C]</sup> Tensile Modulus	2600	MPa	ISO 527
<sup>[C]</sup> Yield stress	50	MPa	ISO 527
<sup>[C]</sup> Yield strain	2.3	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	85	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	12	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

**Thermal properties**

	Value	Unit	Test Standard
--	-------	------	---------------

**ISO Data**

<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	85	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	100	°C	ISO 306

[C]: CAMPUS

**Other properties**

	Value	Unit	Test Standard
--	-------	------	---------------

<sup>[C]</sup> Density	1080	kg/m <sup>3</sup>	ISO 1183
------------------------	------	-------------------	----------

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America, Europe, Asia Pacific, Near East/Africa

**Features**

Copolymer

**Other text information****Injection molding**

Pre-Drying Conditions	80 °C in an air circulating dryer for 3-6 h 80 °C in a dry air (desiccant) dryer for 2-4 h dependant on moisture content
Processing Injection Moulding	melt temperature 220-260 °C mould temperature 50-80 °C
Storage	dry, protected from light not above 30°C