

BAPOLENE® 8015

ABS

Bamberger Polymers, Inc.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	15	cm ³ /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	40	MPa	ASTM D 638
Flexural Modulus	2103	MPa	ASTM D 790
Izod Impact notched, 1/8 in	347	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	97.2	°C	ASTM D 648
Other properties			
Density	1040	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Special Characteristics

High impact or impact modified

Features

High Gloss

Applications

General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa