

BM-533

ABS

Kumho Petrochemical Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	2	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.7	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	44	MPa	ISO 527
Strain at break	32	%	ISO 527
Flexural modulus, 23°C	2100	MPa	ISO 178
Flexural strength	63	MPa	ISO 178
Charpy impact strength, +23°C	24	kJ/m ²	ISO 179/1eU
Izod impact strength, +23°C	23	kJ/m ²	ISO 180/1U
Rockwell hardness	R 102	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	96	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	109	°C	ISO 75-1/-2
Vicat softening temperature, B	112	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-

Other properties	Value	Unit	Test Standard
Density	1050	kg/m ³	ISO 1183

Characteristics**Processing**

Blow Molding

Applications

Automotive

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific