

CA0101C1

ABS

CHIMEI Corporation

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	1000000	Ohm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1060	kg/m ³	ASTM D 792

Film Properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield, MD	40.2	MPa	ASTM D 882
Tensile Strength at Yield, TD	35.3	MPa	ASTM D 882
Tensile Strength at Break, MD	31.4	MPa	ASTM D 882
Tensile Strength at Break, TD	29.4	MPa	ASTM D 882
Elongation at Break, MD	50	%	ASTM D 882
Elongation at Break, TD	30	%	ASTM D 882

Characteristics**Processing**

Sheet Extrusion

Regional Availability

Asia Pacific

Special Characteristics

Increased electrical conductivity