

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	40	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	42	MPa	ISO 527
Yield strain	7	%	ISO 527
Flexural modulus, 23°C	2500	MPa	ISO 178
Flexural strength	70	MPa	ISO 178
Charpy impact strength, +23°C	100	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	11	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	11	kJ/m <sup>2</sup>	ISO 180/1A
Rockwell hardness	R 92	-	ISO 2039-2
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	69	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	78	°C	ISO 75-1/-2
Vicat softening temperature, A	95	°C	ISO 306
Vicat softening temperature, B	90	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.7	mm	-
Yellow Card available	yes	-	-
Burning behav. at thickness h	V-1	class	IEC 60695-11-10
Thickness tested	1.0	mm	-
Yellow Card available	yes	-	-
Burning behav. 5V at thickness h	5VA	class	IEC 60695-11-20
Thickness tested	1.7	mm	-
Yellow Card available	yes	-	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (1)	1	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (2)	2	mm	-
Glow Wire Ignition Temperature (GWIT)	750	°C	IEC 60695-2-13
GWIT - thickness tested (1)	1	mm	-
Glow Wire Ignition Temperature (GWIT)	750	°C	IEC 60695-2-13
GWIT - thickness tested (2)	2	mm	-
<b>Electrical properties</b>			
<b>ISO Data</b>			
Volume resistivity	1E16	Ohm*m	IEC 62631-3-1
Surface resistivity	1E16	Ohm	IEC 62631-3-2
Comparative tracking index	450	-	IEC 60112
<b>Other properties</b>			
Water absorption	0.3	%	Sim. to ISO 62
Density	1190	kg/m <sup>3</sup>	ISO 1183
<b>Processing Recommendation Injection Molding</b>			
Pre-drying - Temperature	70 - 80	°C	-
Pre-drying - Time	0.5 - 2	h	-
Melt temperature	200 - 230	°C	-
Mold temperature	60 - 80	°C	-

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

Flame retardant

**Certifications**

RoHS compliant

**Applications**

Electrical and Electronical

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America