

DENKA GT-R-10

ABS

Denka Company Limited

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	16	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2700	MPa	ISO 527
Yield stress	51	MPa	ISO 527
Stress at break	36	MPa	ISO 527
Flexural modulus, 23°C	2600	MPa	ISO 178
Flexural strength	83	MPa	ISO 178
Charpy notched impact strength, +23°C	21	kJ/m ²	ISO 179/1eA
Rockwell hardness	R 112	-	ISO 2039-2
ASTM Data			
Flexural Modulus	2550	MPa	ASTM D 790
Flexural Strength	76	MPa	ASTM D 790
Rockwell Hardness	R 118	-	ASTM D 785
Izod Impact notched, 1/8 in	196	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	81	°C	ISO 75-1/-2
Vicat softening temperature, B	101	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Yellow Card available	yes	-	-
ASTM Data			
DTUL @ 264 psi	90	°C	ASTM D 648
Vicat Temperature	101	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	1050	kg/m ³	ISO 1183
Density	1040	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 85	°C	-
Pre-drying - Time	2 - 3	h	-
Mold temperature	40 - 60	°C	-
Zone 1	180 - 200	°C	-
Zone 2	190 - 220	°C	-
Zone 3	200 - 240	°C	-
Nozzle temperature	200 - 235	°C	-
Screw speed	80 - 120	rpm	-
Back pressure	0.5 - 1	MPa	-

Characteristics**Processing**

Injection Molding

Features

High Gloss

Regional Availability

North America, Europe, Asia Pacific