

Diamond ABS 3001MC

ABS

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	7.5	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	3.8	kg	-
Mold Shrinkage, MD	0.005	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	43.4	MPa	ASTM D 638
Flexural Modulus	2275	MPa	ASTM D 790
Rockwell Hardness	R 101	-	ASTM D 785
Izod Impact notched, 1/8 in	347	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.52	mm	-
DTUL @ 264 psi	77.8	°C	ASTM D 648
Vicat Temperature	103	°C	ASTM D 1525
Other properties			
Density	1050	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

Platable

Regional Availability

North America