

Diamond ABS 7600B

ABS

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	2.7	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	3.8	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	39.5	MPa	ASTM D 638
Flexural Modulus	2013	MPa	ASTM D 790
Rockwell Hardness	R 102	-	ASTM D 785
Izod Impact notched, 1/8 in	432	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.52	mm	-
DTUL @ 264 psi	77.2	°C	ASTM D 648
Vicat Temperature	104	°C	ASTM D 1525
Other properties			
Density	1030	kg/m ³	ASTM D 792

Characteristics**Processing**

Blow Molding

Regional Availability

North America

Special Characteristics

High impact or impact modified