

**Elix ABS E-LOOP H604 CR**

ABS

Elix Polymers, S.L.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt volume-flow rate, MVR	9	cm <sup>3</sup> /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	2400	MPa	ISO 527
Yield stress	45	MPa	ISO 527
Yield strain	2.6	%	ISO 527
Strain at break	15	%	ISO 527
Flexural modulus, 23°C	2400	MPa	ISO 178
Flexural strength	70	MPa	ISO 178
Charpy impact strength, +23°C	130	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	100	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	20	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	11	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	21	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	12	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-30	°C	-
Ball indentation hardness	102	MPa	ISO 2039-1

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	98	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	102	°C	ISO 75-1/-2
Vicat softening temperature, B	102	°C	ISO 306
Coeff. of linear therm. expansion, parallel	80	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning rate, FMVSS, Thickness 1 mm	60 <sup>(1)</sup>	mm/min	ISO 3795 (FMVSS 302)
Glow Wire Flammability Index (GWFI)	700	°C	IEC 60695-2-12
GWFI - thickness tested (1)	2	mm	-

1: 2 mm

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Relative permittivity, 100Hz	3	-	IEC 62631-2-1
Relative permittivity, 1MHz	2.9	-	IEC 62631-2-1
Dissipation factor, 100Hz	50	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	90	E-4	IEC 62631-2-1
Volume resistivity	1E14	Ohm*m	IEC 62631-3-1
Surface resistivity	1E16	Ohm	IEC 62631-3-2
Electric strength	31	kV/mm	IEC 60243-1
Comparative tracking index	600	-	IEC 60112

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	1040	kg/m <sup>3</sup>	ISO 1183

<b>Test specimen production</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Injection Molding, melt temperature	240	°C	ISO 294
Injection Molding, mold temperature	70	°C	ISO 294
Injection Molding, injection velocity	240	mm/s	ISO 294

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Pellets

**Special Characteristics**

Heat stabilized or stable to heat

**Features**

Low Emission

**Chemical Resistance**

General Chemical Resistance

**Certifications**

Recycled Resin Content, RoHS compliant, ISCC Plus

**Regional Availability**

Europe, Asia Pacific, South and Central America, Near East/Africa