

Elix ABS P2M-AT

ABS

Elix Polymers, S.L.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	22	cm ³ /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2300	MPa	ISO 527
Yield stress	39	MPa	ISO 527
Yield strain	2.1	%	ISO 527
Strain at break	15	%	ISO 527
Flexural modulus, 23°C	2100	MPa	ISO 178
Charpy impact strength, +23°C	180	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	120	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	22	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	11	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	23	kJ/m ²	ISO 180/1A
Izod notched impact strength	11	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-
Ball indentation hardness	95	MPa	ISO 2039-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	93	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	97	°C	ISO 75-1/-2
Vicat softening temperature, B	98	°C	ISO 306
Coeff. of linear therm. expansion, parallel	100	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 100Hz	3.1	-	IEC 62631-2-1
Relative permittivity, 1MHz	3	-	IEC 62631-2-1
Dissipation factor, 100Hz	60	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	80	E-4	IEC 62631-2-1
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E15	Ohm	IEC 62631-3-2
Electric strength	33	kV/mm	IEC 60243-1
Comparative tracking index	600	-	IEC 60112

Other properties	Value	Unit	Test Standard
Density	1040	kg/m ³	ISO 1183

Test specimen production	Value	Unit	Test Standard
ISO Data			
Injection Molding, melt temperature	240	°C	ISO 294
Injection Molding, mold temperature	70	°C	ISO 294
Injection Molding, injection velocity	240	mm/s	ISO 294

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

Anti-static, High impact or impact modified

Certifications

RoHS compliant

Regional Availability

Europe, Asia Pacific, South and Central America, Near East/Africa