

**Elix ABS P2M-V**

ABS

Elix Polymers, S.L.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	18	cm <sup>3</sup> /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	2300	MPa	ISO 527
Yield stress	40	MPa	ISO 527
Yield strain	2.2	%	ISO 527
Strain at break	15	%	ISO 527
Flexural modulus, 23°C	2200	MPa	ISO 178
Charpy impact strength, +23°C	180	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	120	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	22	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	11	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	23	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	11	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-30	°C	-
Ball indentation hardness	100	MPa	ISO 2039-1

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	93	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	98	°C	ISO 75-1/-2
Vicat softening temperature, B	97	°C	ISO 306
Coeff. of linear therm. expansion, parallel	100	E-6/K	ISO 11359-1/-2

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Relative permittivity, 100Hz	3	-	IEC 62631-2-1
Relative permittivity, 1MHz	2.9	-	IEC 62631-2-1
Dissipation factor, 100Hz	50	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	80	E-4	IEC 62631-2-1
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E13	Ohm	IEC 62631-3-2
Electric strength	39	kV/mm	IEC 60243-1
Comparative tracking index	600	-	IEC 60112

Test specimen production	Value	Unit	Test Standard
<b>ISO Data</b>			
Injection Molding, melt temperature	240	°C	ISO 294
Injection Molding, mold temperature	70	°C	ISO 294
Injection Molding, injection velocity	240	mm/s	ISO 294

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

High impact or impact modified

**Certifications**

RoHS compliant

**Regional Availability**

Europe, Asia Pacific, South and Central America, Near East/Africa