

Elix Ultra HH 4105

ABS

Elix Polymers, S.L.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	14	cm ³ /10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.7	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2000	MPa	ISO 527
Yield stress	45	MPa	ISO 527
Yield strain	3.7	%	ISO 527
Nominal strain at break	15	%	ISO 527
Stress at break	37	MPa	ISO 527
Strain at break	30	%	ISO 527
Flexural modulus, 23°C	2000	MPa	ISO 178
Charpy notched impact strength, +23°C	40	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	30	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	42	kJ/m ²	ISO 180/1A
Izod notched impact strength	34	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-
Ball indentation hardness	85	MPa	ISO 2039-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	99	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	108	°C	ISO 75-1/-2
Vicat softening temperature, B	106	°C	ISO 306
Coeff. of linear therm. expansion, parallel	90	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	90	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 100Hz	3	-	IEC 62631-2-1
Relative permittivity, 1MHz	3	-	IEC 62631-2-1
Dissipation factor, 100Hz	38	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	86	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2

Test specimen production	Value	Unit	Test Standard
ISO Data			
Injection Molding, melt temperature	240	°C	ISO 294
Injection Molding, mold temperature	70	°C	ISO 294
Injection Molding, injection velocity	240	mm/s	ISO 294

Characteristics**Processing**

Injection Molding

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Certifications

RoHS compliant

Regional Availability

Europe, Asia Pacific, South and Central America, Near East/Africa