

**Excelloy DX220**

ABS

Techno-UMG Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	30	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Strength	47	MPa	ISO 527
Flexural modulus, 23°C	1870	MPa	ISO 178
Flexural strength	67	MPa	ISO 178
Charpy impact strength, +23°C	9	kJ/m <sup>2</sup>	ISO 179/1eU
Rockwell hardness	R 84	-	ISO 2039-2

<b>ASTM Data</b>			
Tensile Strength	49	MPa	ASTM D 638
Flexural Modulus	2260	MPa	ASTM D 790
Flexural Strength	76.5	MPa	ASTM D 790
Rockwell Hardness	R 85	-	ASTM D 785

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	HB	-	UL 94

Other properties	Value	Unit	Test Standard
Density	1070	kg/m <sup>3</sup>	ISO 1183
Density	1070	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 90	°C	-
Pre-drying - Time	2 - 5	h	-
Mold temperature	40 - 80	°C	-
Zone 1	190 - 260	°C	-

**Characteristics****Processing**

Injection Molding, Profile Extrusion, Coating

**Regional Availability**

North America, Asia Pacific