

ISOTER® A 10 120 HT

ABS

Sirmax S.p.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	10	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	45	MPa	ISO 527
Strain at break	10	%	ISO 527
Flexural modulus, 23°C	2500	MPa	ISO 178
Flexural strength	80	MPa	ISO 178
Charpy impact strength, +23°C	105	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	12	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	12	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	92	°C	ISO 75-1/-2
Vicat softening temperature, B	102	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E16	Ohm*m	IEC 62631-3-1
Surface resistivity	1E14	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Density	1050	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	70 - 80	°C	-
Pre-drying - Time	0.5 - 2	h	-
Melt temperature	210 - 240	°C	-
Mold temperature	60 - 80	°C	-

Characteristics**Processing**

Injection Molding

Certifications

RoHS compliant

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific, South and Central America