

KRALASTIC™ AN-435

ABS

Nippon A&L Inc.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	13	cm ³ /10min	ISO 1133
Temperature	200	°C	-
Load	5	kg	-
Other Standards^[S]			
Molding shrinkage, parallel	0.5	%	Producer Method

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	48	MPa	ISO 527
Flexural modulus, 23°C	2400	MPa	ISO 178
Flexural strength	74	MPa	ISO 178
Charpy notched impact strength, +23°C	15	kJ/m ²	ISO 179/1eA
Rockwell hardness	R 112	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	74	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	78	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-2	class	IEC 60695-11-10
Thickness tested	1.5	mm	-

Other properties	Value	Unit	Test Standard
Density	1060	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	75 - 85	°C	-
Pre-drying - Time	3 - 6	h	-
Melt temperature	200 - 230	°C	-
Mold temperature	40 - 60	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

Asia Pacific

Special Characteristics

Flame retardant, Halogen-free