

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	19980	MPa	ASTM D 638
Tensile Strength at Break	106	MPa	ASTM D 638
Elongation at Break	1	%	ASTM D 638
Flexural Modulus	18090	MPa	ASTM D 790
Flexural Strength	179	MPa	ASTM D 790
Izod Impact notched, 1/8 in	42	J/m	ASTM D 256

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	1000000	Ohm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1270	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

Asia Pacific

Special Characteristics

Increased electrical conductivity