

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	13	cm ³ /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Melt flow index, MFI	13	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2100	MPa	ISO 527
Yield stress	47	MPa	ISO 527
Yield strain	2.7	%	ISO 527
Flexural modulus, 23°C	2100	MPa	ISO 178
Charpy notched impact strength, +23°C	19	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	10	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	21	kJ/m ²	ISO 180/1A
Izod notched impact strength	9	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Vicat softening temperature, B	101	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-

Other properties	Value	Unit	Test Standard
Density	1050	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Special Characteristics

Platable

Features

Color Stability

Applications

Automotive

Regional Availability

Europe, Asia Pacific, Near East/Africa