

**NH-627**

ABS

Kingfa Sci. &amp; Tech.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>5</b>	g/10min	ASTM D 1238
Temperature	<b>200</b>	°C	-
Load	<b>5</b>	kg	-
Mold Shrinkage, MD	<b>0.0055</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength	<b>45</b>	MPa	ASTM D 638
Flexural Modulus	<b>2500</b>	MPa	ASTM D 790
Flexural Strength	<b>70</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 102</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>139</b>	J/m	ASTM D 256
Izod Impact notched, 1/4 in	<b>120</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-2</b>	-	UL 94
Thickness tested	<b>1.6</b>	mm	-
DTUL @ 66 psi	<b>80</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>72</b>	°C	ASTM D 648
<b>Electrical properties</b>			
<b>ASTM Data</b>			
Dielectric Strength, Short Time	<b>22</b>	kV/mm	ASTM D 149
Volume Resistivity	<b>1E14</b>	Ohm*cm	ASTM D 257
<b>Other properties</b>			
Density	<b>1060</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets

**Special Characteristics**

Flame retardant

**Applications**

Electrical and Electronical

**Regional Availability**

Asia Pacific