

Novodur® 250

ABS

INEOS Styrolution

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	38	cm ³ /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	49	MPa	ISO 527

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Vicat Temperature	99	°C	ASTM D 1525

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Applications

Electrical and Electronical, Sports Equipment

Regional Availability

Asia Pacific