

STAREX VG-4910

ABS-GF

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	23	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
ASTM Data			
Melt Flow Index, MFI	23	g/10min	ASTM D 1238
Temperature	220	°C	-
Load	10	kg	-
Mold Shrinkage, MD	0.002	mm/mm	ASTM D 955
Mechanical properties			
ISO Data			
Yield stress	85	MPa	ISO 527
Flexural modulus, 23°C	4100	MPa	ISO 178
Flexural strength	100	MPa	ISO 178
Charpy notched impact strength, +23°C	7	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	7	kJ/m ²	ISO 180/1A
Rockwell hardness	R 109	-	ISO 2039-2
ASTM Data			
Tensile Modulus	3700	MPa	ASTM D 638
Tensile Strength at Yield	74	MPa	ASTM D 638
Tensile Strength at Break	76	MPa	ASTM D 638
Elongation at Break	3.4	%	ASTM D 638
Flexural Modulus	3600	MPa	ASTM D 790
Flexural Strength	78	MPa	ASTM D 790
Rockwell Hardness	R 109	-	ASTM D 785
Izod Impact notched, 1/8 in	69	J/m	ASTM D 256
Izod Impact notched, 1/4 in	120	J/m	ASTM D 256
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	92	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	101	°C	ISO 75-1/-2
Vicat softening temperature, B	99	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	2.5	mm	-
Burning behav. 5V at thickness h	5VA	class	IEC 60695-11-20
Thickness tested	2.5	mm	-
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.6	mm	-
DTUL @ 66 psi	102	°C	ASTM D 648
DTUL @ 264 psi	97	°C	ASTM D 648
Other properties			
Density	1120	kg/m ³	ISO 1183
Density	1120	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.005	%	-
Melt temperature	235	°C	-
Mold temperature	40 - 80	°C	-

STAREX VG-4910

ABS-GF

Lotte Chemical Corporation

Zone 1	180 - 190	°C	-
Zone 2	200 - 210	°C	-
Zone 3	220 - 230	°C	-
Nozzle temperature	240	°C	-
Screw speed	50 - 150	rpm	-
Injection pressure	49 - 250	MPa	-
Back pressure	0.5 - 2	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Delivery form

Pellets, Natural Color