

STAREX VG-4920F

ABS-GF

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	41	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
ASTM Data			
Melt Flow Index, MFI	42	g/10min	ASTM D 1238
Temperature	220	°C	-
Load	10	kg	-
Mold Shrinkage, MD	0.002	mm/mm	ASTM D 955
Mechanical properties			
ISO Data			
Tensile Modulus	6100	MPa	ISO 527
Yield stress	102	MPa	ISO 527
Stress at break	101	MPa	ISO 527
Strain at break	2.4	%	ISO 527
Flexural modulus, 23°C	7100	MPa	ISO 178
Flexural strength	146	MPa	ISO 178
Charpy notched impact strength, +23°C	9.2	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	9.1	kJ/m ²	ISO 180/1A
Rockwell hardness	R 116	-	ISO 2039-2
ASTM Data			
Tensile Modulus	5900	MPa	ASTM D 638
Tensile Strength at Yield	85	MPa	ASTM D 638
Tensile Strength at Break	98	MPa	ASTM D 638
Elongation at Break	2.8	%	ASTM D 638
Flexural Modulus	5700	MPa	ASTM D 790
Flexural Strength	100	MPa	ASTM D 790
Rockwell Hardness	R 110	-	ASTM D 785
Izod Impact notched, 1/8 in	59	J/m	ASTM D 256
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	95	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	100	°C	ISO 75-1/-2
Vicat softening temperature, B	102	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	2.0	mm	-
Burning behav. 5V at thickness h	5VA	class	IEC 60695-11-20
Thickness tested	2.0	mm	-
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.6	mm	-
DTUL @ 66 psi	100	°C	ASTM D 648
DTUL @ 264 psi	93	°C	ASTM D 648
Other properties			
Density	1340	kg/m ³	ISO 1183
Density	1330	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2	h	-
Processing humidity	≤0.07	%	-
Melt temperature	230	°C	-

STAREX VG-4920F

ABS-GF

Lotte Chemical Corporation

Mold temperature	60 - 80	°C	-
Zone 1	220	°C	-
Zone 2	220	°C	-
Zone 3	230	°C	-
Nozzle temperature	240	°C	-
Screw speed	50 - 100	rpm	-
Injection pressure	93	MPa	-
Back pressure	0.5 - 2.9	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Delivery form

Pellets, Natural Color