

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	0.7	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Modulus	4900	MPa	ASTM D 638
Tensile Strength at Yield	76	MPa	ASTM D 638
Tensile Strength at Break	76	MPa	ASTM D 638
Elongation at Yield	3	%	ASTM D 638
Elongation at Break	4	%	ASTM D 638
Flexural Modulus	8000	MPa	ASTM D 790
Flexural Strength	100	MPa	ASTM D 790

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	99	°C	ASTM D 648
DTUL @ 264 psi	91	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1260	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Regional Availability

North America