

**Product Texts**

Base Polymer	Acrylonitrile/Butadiene/Styrene/Copolymer
Filler/Additive System	15 % special filler
Special Features	highly reflective,opaque,good flow
Market Segment	Automotive,Lighting
Application Area	lighting,light blocking components
Typical Applications	light guides,reflectors

**Processing/Physical Characteristics**

	Value	Unit	Test Standard
--	-------	------	---------------

**ISO Data**

<sup>[C]</sup> Melt volume-flow rate, MVR	25	cm <sup>3</sup> /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-

[C]: CAMPUS

**Mechanical properties**

	Value	Unit	Test Standard
--	-------	------	---------------

**ISO Data**

<sup>[C]</sup> Tensile Modulus	2600	MPa	ISO 527
<sup>[C]</sup> Yield stress	41	MPa	ISO 527
<sup>[C]</sup> Yield strain	2.1	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	50	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	9	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

**Thermal properties**

	Value	Unit	Test Standard
--	-------	------	---------------

**ISO Data**

<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	85	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	95	°C	ISO 306

[C]: CAMPUS

**Other properties**

	Value	Unit	Test Standard
--	-------	------	---------------

<sup>[C]</sup> Density	1170	kg/m <sup>3</sup>	ISO 1183
------------------------	------	-------------------	----------

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Features**

Light Blocking

**Delivery form**

White

**Regional Availability**

North America, Europe, Asia Pacific, Near East/Africa

**Other text information****Injection molding**

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-4 h 80 °C in an air circulating dryer for 4-8 h max. moisture content <0,02 %
Processing Injection Moulding	melt temperature 220-260 °C mould temperature 50-80 °C
Storage	dry, protected from light