

Novodur® 680

ABS

INEOS Styrolution

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	6	cm ³ /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	46	MPa	ISO 527

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Vicat Temperature	98	°C	ASTM D 1525

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Special Characteristics

High impact or impact modified

Chemical Resistance

General Chemical Resistance

Applications

Electrical and Electronical, Sports Equipment

Regional Availability

Asia Pacific