

PermaStat® 600 UV

ABS

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2068	MPa	ASTM D 638
Tensile Strength	41.4	MPa	ASTM D 638
Flexural Modulus	1724	MPa	ASTM D 790
Flexural Strength	68.9	MPa	ASTM D 790
Izod Impact notched, 1/8 in	267	J/m	ASTM D 256

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	9.9E11	Ohm	ASTM D 257
Volume Resistivity	9.9E10	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1060	kg/m ³	ASTM D 792
Moisture Content	0.1	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	82.2	°C	-
Pre-drying - Time	2	h	-
Melt temperature	199 - 238	°C	-
Mold temperature	48.9 - 93.3	°C	-
Injection pressure	68.9 - 103	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

Anti-static, U.V. stabilized or stable to weather