

POLYabs F00L

ABS

Polykemi AB

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	18	g/10min	ISO 1133
Temperature	230	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.7	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	40	MPa	ISO 527
Yield strain	6	%	ISO 527
Flexural modulus, 23°C	2100	MPa	ISO 178
Charpy notched impact strength, +23°C	17	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	76	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	87	°C	ISO 75-1/-2
Vicat softening temperature, A	105	°C	ISO 306
Vicat softening temperature, B	100	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Yellow Card available	yes	-	-

Other properties	Value	Unit	Test Standard
Density	1040	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Regional Availability

Europe, Asia Pacific

Delivery form

Granules