

POLYabs V0X

ABS

Polykemi AB

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	18	g/10min	ISO 1133
Temperature	230	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Strength	40	MPa	ISO 527
Yield strain	6	%	ISO 527
Flexural modulus, 23°C	2000	MPa	ISO 178
Charpy notched impact strength, +23°C	16	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	74	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	84	°C	ISO 75-1/-2
Vicat softening temperature, A	98	°C	ISO 306
Vicat softening temperature, B	85	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3.2	mm	-
Yellow Card available	yes	-	-
Glow Wire Ignition Temperature (GWIT)	960	°C	IEC 60695-2-13
GWIT - thickness tested (1)	2.5	mm	-
Other properties			
Density	1160	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Special Characteristics

Flame retardant

Delivery form

Granules

Regional Availability

Europe, Asia Pacific