

**POLYLAC PA-756**

ABS

CHIMEI Corporation

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt volume-flow rate, MVR	<b>42</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>220</b>	°C	-
Load	<b>10</b>	kg	-
Molding shrinkage, parallel	<b>0.6</b>	%	ISO 294-4, 2577
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>4.4</b>	g/10min	ASTM D 1238
Temperature	<b>200</b>	°C	-
Load	<b>5</b>	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	<b>44</b>	MPa	ISO 527
Stress at break	<b>32</b>	MPa	ISO 527
Flexural modulus, 23°C	<b>2100</b>	MPa	ISO 178
Flexural strength	<b>72</b>	MPa	ISO 178
Charpy notched impact strength, +23°C	<b>15</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	<b>9</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	<b>14</b>	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	<b>8</b>	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	<b>-30</b>	°C	-
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>46.9</b>	MPa	ASTM D 638
Flexural Modulus	<b>2551</b>	MPa	ASTM D 790
Flexural Strength	<b>74.3</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 115</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>171</b>	J/m	ASTM D 256
Izod Impact notched, 1/4 in	<b>160</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>83</b>	°C	ISO 75-1/-2
Vicat softening temperature, A	<b>104</b>	°C	ISO 306
Vicat softening temperature, B	<b>96</b>	°C	ISO 306
Coeff. of linear therm. expansion, parallel	<b>89</b>	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>1.5</b>	mm	-
Yellow Card available	<b>yes</b>	-	-
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94
Thickness tested	<b>1.5</b>	mm	-
DTUL @ 264 psi	<b>82.8</b>	°C	ASTM D 648
Vicat Temperature	<b>105</b>	°C	ASTM D 1525
<b>Electrical properties</b>			
<b>ASTM Data</b>			
Arc Resistance	<b>90</b>	s	ASTM D 495
<b>Other properties</b>			
Density	<b>1050</b>	kg/m <sup>3</sup>	ISO 1183
Density	<b>1050</b>	kg/m <sup>3</sup>	ASTM D 792
<b>Processing Recommendation Injection Molding</b>			
Pre-drying - Temperature	<b>80 - 85</b>	°C	-
Pre-drying - Time	<b>2 - 4</b>	h	-
Mold temperature	<b>30 - 70</b>	°C	-
Feed temperature	<b>180 - 220</b>	°C	-

**POLYLAC PA-756**

ABS

CHIMEI Corporation

Zone 1	<b>190 - 230</b>	°C	-
Nozzle temperature	<b>190 - 230</b>	°C	-

**Characteristics****Processing**

Injection Molding

**Features**

High Gloss

**Delivery form**

Pellets

**Regional Availability**

Asia Pacific