

Product Texts

High impact ABS for extrusion and injection moulding

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	7	cm ³ /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	1500	MPa	ISO 527
^[C] Yield stress	40	MPa	ISO 527
^[C] Yield strain	2.5	%	ISO 527
^[C] Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	34	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	19	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	88	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	93	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	90	°C	ISO 306
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E11	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	>1E15	Ohm	IEC 62631-3-2
^[C] Comparative tracking index	600	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1030	kg/m ³	ISO 1183

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	220 - 260	°C	-
Mold temperature	40 - 80	°C	-

Characteristics

Processing

Injection Molding, Profile Extrusion, Sheet Extrusion, Other Extrusion, Thermoforming

Delivery form

Granules

Additives

Release agent

Special Characteristics

Platable, High impact or impact modified

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information**Injection molding****PREPROCESSING; Pretreatment**

Predrying: 3-4h / 80°C

PROCESSING ;Processing:

Melttemperature	220 - 260	°C
Mouldtemperature	40 - 80	°C