

**RamShine PV700CR32**

ABS

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	19	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
<b>Other Standards<sup>[S]</sup></b>			
Molding shrinkage, parallel	0.6	%	Producer Method

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	2200	MPa	ISO 527
Tensile Strength	40	MPa	ISO 527
Izod notched impact strength, +23°C	21	kJ/m <sup>2</sup>	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-

Other properties	Value	Unit	Test Standard
Density	1050	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.1	%	-
Mold temperature	40 - 80	°C	-
Feed temperature	60 - 70	°C	-
Zone 1	200 - 220	°C	-
Zone 2	200 - 220	°C	-
Zone 3	210 - 240	°C	-

**Characteristics****Processing**

Injection Molding

**Certifications**

RoHS compliant

**Special Characteristics**

U.V. stabilized or stable to weather

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa