

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>88</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	<b>94</b>	°C	ISO 306
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>1.6</b>	mm	-

[C]: CAMPUS

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Surface resistivity	<b>&gt;1E15</b>	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	<b>27</b>	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	<b>600</b>	-	IEC 60112

[C]: CAMPUS

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>1050</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

**Processing**

Other Extrusion

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa