

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	7	cm <sup>3</sup> /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	1900	MPa	ISO 527
Tensile Strength	40	MPa	ISO 527
Strain at break	4	%	ISO 527
Charpy impact strength, +23°C	100	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	100	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	28	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	14	kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact strength, +23°C	100	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	30	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	15	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-30	°C	-
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	92	°C	ISO 75-1/-2
Vicat softening temperature, B	96	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
<b>Other properties</b>			
<b>Value</b>			
Density	1020	kg/m <sup>3</sup>	ISO 1183
Moisture Content	0.2	%	-

## Characteristics

### Processing

Injection Molding

### Features

Low Odor

### Delivery form

Pellets, Natural Color

### Regional Availability

Europe

### Special Characteristics

Anti-static, High impact or impact modified, Light stabilized or stable to light