

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	5	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
ASTM Data			
Mold Shrinkage, MD	0.0055	mm/mm	ASTM D 955
Mechanical properties			
Value	Unit	Test Standard	
ISO Data			
Yield stress	36	MPa	ISO 527
Stress at break	28	MPa	ISO 527
Strain at break	22	%	ISO 527
Flexural modulus, 23°C	2000	MPa	ISO 178
Izod notched impact strength, +23°C	35	kJ/m ²	ISO 180/1A
Izod notched impact strength	16	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-
Thermal properties			
Value	Unit	Test Standard	
ISO Data			
Temp. of deflection under load, 1.80 MPa	83	°C	ISO 75-1/-2
Vicat softening temperature, A	96	°C	ISO 306
Vicat softening temperature, B	90	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.2	mm	-
Glow Wire Flammability Index (GWFI)	650	°C	IEC 60695-2-12
GWFI - thickness tested (1)	2	mm	-
Electrical properties			
Value	Unit	Test Standard	
ISO Data			
Volume resistivity	1E12	Ohm*m	IEC 62631-3-1
Surface resistivity	1E15	Ohm	IEC 62631-3-2
Electric strength	30	kV/mm	IEC 60243-1
Comparative tracking index	600	-	IEC 60112
Other properties			
Value	Unit	Test Standard	
Density	1050	kg/m ³	ISO 1183

Characteristics

Processing

Other Extrusion

Regional Availability

Europe

Special Characteristics

High impact or impact modified