

STAREX CM-0140UV

ABS

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	3	g/10min	ISO 1133
Temperature	200	°C	-
Load	5	kg	-
ASTM Data			
Melt Flow Index, MFI	3	g/10min	ASTM D 1238
Temperature	200	°C	-
Load	5	kg	-
Mechanical properties			
ISO Data			
Yield stress	45	MPa	ISO 527
Flexural modulus, 23°C	2000	MPa	ISO 178
Flexural strength	65	MPa	ISO 178
Charpy notched impact strength, +23°C	20	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	20	kJ/m ²	ISO 180/1A
Rockwell hardness	R 109	-	ISO 2039-2
ASTM Data			
Tensile Strength at Yield	42	MPa	ASTM D 638
Flexural Modulus	2100	MPa	ASTM D 790
Flexural Strength	63	MPa	ASTM D 790
Rockwell Hardness	R 109	-	ASTM D 785
Izod Impact notched, 1/4 in	200	J/m	ASTM D 256
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	75	°C	ISO 75-1/-2
Vicat softening temperature, B	95	°C	ISO 306
ASTM Data			
DTUL @ 264 psi	76	°C	ASTM D 648
Other properties			
Density	1040	kg/m ³	ISO 1183
Density	1040	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.05	%	-
Melt temperature	230	°C	-
Mold temperature	40 - 80	°C	-
Zone 1	160 - 180	°C	-
Zone 2	190 - 200	°C	-
Zone 3	210 - 220	°C	-
Screw speed	50 - 150	rpm	-
Injection pressure	49 - 150	MPa	-
Back pressure	0.5 - 2	MPa	-

Characteristics**Processing**

Injection Molding

Special Characteristics

U.V. stabilized or stable to weather

Delivery form

Pellets, Natural Color

Regional Availability

North America, Europe, Asia Pacific