

STAREX LH-0300

ABS

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	10	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577
ASTM Data			
Melt Flow Index, MFI	10	g/10min	ASTM D 1238
Temperature	220	°C	-
Load	10	kg	-
Mold Shrinkage, MD	0.0055	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.0055	mm/mm	ASTM D 955
Mechanical properties			
ISO Data			
Tensile Modulus	1890	MPa	ISO 527
Yield stress	36	MPa	ISO 527
Stress at break	34	MPa	ISO 527
Strain at break	60	%	ISO 527
Flexural modulus, 23°C	2060	MPa	ISO 178
Flexural strength	58	MPa	ISO 178
Charpy notched impact strength, +23°C	16	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	17	kJ/m ²	ISO 180/1A
Rockwell hardness	R 100	-	ISO 2039-2
ASTM Data			
Tensile Modulus	1700	MPa	ASTM D 638
Tensile Strength at Yield	35	MPa	ASTM D 638
Tensile Strength at Break	32	MPa	ASTM D 638
Elongation at Break	51	%	ASTM D 638
Flexural Modulus	1700	MPa	ASTM D 790
Flexural Strength	46	MPa	ASTM D 790
Rockwell Hardness	R 100	-	ASTM D 785
Izod Impact notched, 1/8 in	150	J/m	ASTM D 256
Izod Impact notched, 1/4 in	98	J/m	ASTM D 256
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	80	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	94	°C	ISO 75-1/-2
Vicat softening temperature, B	100	°C	ISO 306
ASTM Data			
DTUL @ 66 psi	99	°C	ASTM D 648
DTUL @ 264 psi	88	°C	ASTM D 648
Other properties			
Density	1040	kg/m ³	ISO 1183
Density	1040	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.1	%	-
Melt temperature	230 - 250	°C	-
Mold temperature	40 - 80	°C	-
Zone 1	180 - 200	°C	-
Zone 2	200 - 220	°C	-
Zone 3	210 - 230	°C	-

STAREX LH-0300

ABS

Lotte Chemical Corporation

Nozzle temperature	230 - 250	°C	-
Screw speed	50 - 100	rpm	-
Injection pressure	49 - 150	MPa	-
Back pressure	0.5 - 2	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Delivery form

Pellets, Natural Color