

STAREX NH-0825 S

ABS

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	6.5	g/10min	ISO 1133
Temperature	200	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Molding shrinkage, normal	0.5	%	ISO 294-4, 2577
ASTM Data			
Melt Flow Index, MFI	6.5	g/10min	ASTM D 1238
Temperature	200	°C	-
Load	5	kg	-
Mold Shrinkage, MD	0.005	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.005	mm/mm	ASTM D 955
Mechanical properties			
ISO Data			
Tensile Modulus	2400	MPa	ISO 527
Yield stress	41	MPa	ISO 527
Stress at break	34	MPa	ISO 527
Strain at break	12	%	ISO 527
Flexural modulus, 23°C	2400	MPa	ISO 178
Flexural strength	70	MPa	ISO 178
Charpy notched impact strength, +23°C	24	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	18	kJ/m ²	ISO 180/1A
Rockwell hardness	R 113	-	ISO 2039-2
ASTM Data			
Tensile Modulus	2100	MPa	ASTM D 638
Tensile Strength at Yield	41	MPa	ASTM D 638
Tensile Strength at Break	39	MPa	ASTM D 638
Elongation at Break	15	%	ASTM D 638
Flexural Modulus	2300	MPa	ASTM D 790
Flexural Strength	63	MPa	ASTM D 790
Rockwell Hardness	R 105	-	ASTM D 785
Izod Impact notched, 1/8 in	210	J/m	ASTM D 256
Izod Impact notched, 1/4 in	200	J/m	ASTM D 256
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	74	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	87	°C	ISO 75-1/-2
Vicat softening temperature, B	93	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-2	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Burning behav. at thickness h	V-2	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
ASTM Data			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	0.75	mm	-
Other properties			
Density	1050	kg/m ³	ISO 1183
Density	1050	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4 - 6	h	-
Processing humidity	≤0.4	%	-
Melt temperature	220 - 230	°C	-

STAREX NH-0825 S

ABS

Lotte Chemical Corporation

Mold temperature	60 - 80	°C	-
Zone 1	180 - 210	°C	-
Zone 2	210	°C	-
Zone 3	210	°C	-
Nozzle temperature	220	°C	-
Screw speed	40 - 80	rpm	-
Injection pressure	78	MPa	-
Back pressure	1 - 2.9	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Delivery form

Pellets, Natural Color