

STAREX SD-0150 U

ABS

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	1.7	g/10min	ISO 1133
Temperature	200	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	0.3	%	ISO 294-4, 2577
ASTM Data			
Melt Flow Index, MFI	1.7	g/10min	ASTM D 1238
Temperature	200	°C	-
Load	5	kg	-
Mold Shrinkage, MD	0.003	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.003	mm/mm	ASTM D 955
Mechanical properties			
ISO Data			
Tensile Modulus	2400	MPa	ISO 527
Yield stress	41	MPa	ISO 527
Stress at break	35	MPa	ISO 527
Strain at break	14	%	ISO 527
Flexural modulus, 23°C	2100	MPa	ISO 178
Flexural strength	59	MPa	ISO 178
Charpy notched impact strength, +23°C	28	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	24	kJ/m ²	ISO 180/1A
Rockwell hardness	R 108	-	ISO 2039-2
ASTM Data			
Tensile Modulus	2000	MPa	ASTM D 638
Tensile Strength at Yield	40	MPa	ASTM D 638
Tensile Strength at Break	44	MPa	ASTM D 638
Elongation at Break	15	%	ASTM D 638
Flexural Modulus	2100	MPa	ASTM D 790
Flexural Strength	58	MPa	ASTM D 790
Rockwell Hardness	R 108	-	ASTM D 785
Izod Impact notched, 1/8 in	280	J/m	ASTM D 256
Izod Impact notched, 1/4 in	240	J/m	ASTM D 256
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	78	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	91	°C	ISO 75-1/-2
Vicat softening temperature, B	98	°C	ISO 306
ASTM Data			
DTUL @ 66 psi	95	°C	ASTM D 648
DTUL @ 264 psi	83	°C	ASTM D 648
Other properties			
Value			
Density	1040	kg/m ³	ISO 1183
Density	1040	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Value			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.05	%	-
Melt temperature	230	°C	-
Mold temperature	40 - 80	°C	-
Zone 1	160 - 180	°C	-
Zone 2	190 - 200	°C	-
Zone 3	210 - 220	°C	-

STAREX SD-0150 U

ABS

Lotte Chemical Corporation

Nozzle temperature	230	°C	-
Screw speed	50 - 150	rpm	-
Injection pressure	49 - 150	MPa	-
Back pressure	0.5 - 2	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Delivery form

Pellets, Natural Color