

STAREX SD-0150UF

ABS

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	11	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
ASTM Data			
Melt Flow Index, MFI	11	g/10min	ASTM D 1238
Temperature	220	°C	-
Load	10	kg	-
Mechanical properties			
ISO Data			
Yield stress	35	MPa	ISO 527
Flexural modulus, 23°C	1500	MPa	ISO 178
Flexural strength	48	MPa	ISO 178
Charpy notched impact strength, +23°C	26	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	28	kJ/m ²	ISO 180/1A
Rockwell hardness	R 104	-	ISO 2039-2
ASTM Data			
Tensile Modulus	2000	MPa	ASTM D 638
Tensile Strength at Yield	36	MPa	ASTM D 638
Tensile Strength at Break	31	MPa	ASTM D 638
Elongation at Break	16	%	ASTM D 638
Flexural Modulus	1800	MPa	ASTM D 790
Flexural Strength	49	MPa	ASTM D 790
Rockwell Hardness	R 104	-	ASTM D 785
Izod Impact notched, 1/8 in	350	J/m	ASTM D 256
Izod Impact notched, 1/4 in	280	J/m	ASTM D 256
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	79	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	90	°C	ISO 75-1/-2
Vicat softening temperature, B	98	°C	ISO 306
ASTM Data			
DTUL @ 66 psi	95	°C	ASTM D 648
DTUL @ 264 psi	84	°C	ASTM D 648
Other properties			
Density	1040	kg/m ³	ISO 1183
Density	1040	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.05	%	-
Melt temperature	230	°C	-
Mold temperature	40 - 80	°C	-
Zone 1	160 - 180	°C	-
Zone 2	190 - 200	°C	-
Zone 3	210 - 220	°C	-
Nozzle temperature	230	°C	-
Screw speed	50 - 150	rpm	-
Injection pressure	49 - 150	MPa	-
Back pressure	0.5 - 2	MPa	-

STAREX SD-0150UF

ABS

Lotte Chemical Corporation

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Delivery form

Pellets, Natural Color