

Stylac IC10N

ABS

Asahi Kasei

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	1	cm ³ /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Melt flow index, MFI	2	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
ASTM Data			
Mold Shrinkage, MD	0.0015	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Flexural modulus, 23°C	10000	MPa	ISO 178
Flexural strength	186	MPa	ISO 178
Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	100	°C	ISO 75-1/-2
Vicat softening temperature, B	110	°C	ISO 306
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
Thermal Conductivity, solid state	0.0375	W/(m K)	ASTM C 177

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	4	Ohm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1120	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	75 - 90	°C	-
Pre-drying - Time	3 - 4	h	-
Mold temperature	40 - 70	°C	-
Zone 1	200 - 230	°C	-
Zone 2	200 - 240	°C	-
Zone 3	220 - 260	°C	-
Nozzle temperature	210 - 245	°C	-
Maximum residence time	20	min	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

Increased electrical conductivity