

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	6	g/10min	ASTM D 1238
Temperature	220	°C	-
Load	10	kg	-
Mold Shrinkage, MD	0.0055	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength	44	MPa	ASTM D 638
Flexural Modulus	2260	MPa	ASTM D 790
Flexural Strength	73	MPa	ASTM D 790
Rockwell Hardness	R 102	-	ASTM D 785
Izod Impact notched, 1/4 in	431	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.6	mm	-
DTUL @ 264 psi	88	°C	ASTM D 648
Vicat Temperature	101	°C	ASTM D 1525
Other properties			
Density	1040	kg/m ³	ASTM D 792
Processing Recommendation Extrusion			
Pre-drying - Temperature	70 - 80	°C	-
Pre-drying - Time	2 - 3	h	-
Melt temperature	180 - 230	°C	-
Zone 1	70 - 80	°C	-
Zone 2	80 - 90	°C	-
Zone 3	90 - 110	°C	-

Characteristics

Processing

Other Extrusion

Regional Availability

Asia Pacific

Special Characteristics

High impact or impact modified